


SCB SAMPLE PREPARATION SAW HYQG-S1

Used to cut a gap with a width of 1.5mm and a depth of 15mm for the specimen of asphalt mixture crack growth performance test (Semi Circular Bend method) and asphalt mixture low temperature performance test (Semi Circular Bend method).

SCB SAMPLE PREPARATION SAW HYOG-S1

TECHNICAL SPECIFICATIONS

Cutting device power	450W
Saw blade diameter	φ105mm
Cutting accuracy	±0.1mm
Specimen size	φ150mm semicircle
Cutting width	1.5±0.1(mm)
Cutting depth	15±1(mm)
Power supply	AC220V 50Hz
Dimensions	450x350x420(mm)
Weight	30Kg





FEATURES

- Simple operation, stable running and low noise.
- Customized saw blade with linear moving units to ensure cutting accuracy.
- With a protective cover, it is safer and cleaner to use.
- Saw blade speed is adjustable.
- Small size.